

UNDERLOCK[®] RUBBER TILE

Johnsonite[®]

A Tarkett Company

Installation Instructions

Triumph and Inertia™

Handling and Storage

- 1. Johnsonite flooring and adhesives must be site conditioned at room temperature for 48 hours prior to, during, and after installation. Room temperature must be maintained between 65° and 85°F (18° and 30°C) with HVAC system operating. A minimum temperature of 55°F (13°C) must be maintained afterwards. The ambient relative humidity should be between 40% and 60%.
- **2.** In areas that are exposed to intense or direct sunlight, the product must be protected
- during the conditioning, installation, and adhesive curing periods, by covering the light source.
- **3.** The highest quality of materials and workmanship is employed in the manufacture of Johnsonite Flooring and careful inspection is made before shipment. However, a quality installation is the responsibility of the installer. It is the installer's responsibility to verify the accuracy of the order and to ensure the materials are checked for damage, defects,
- and satisfactory color match. An authorized Johnsonite distributor or Johnsonite representative must be notified of any defects before installation proceeds.
- 4. Johnsonite cannot accept responsibility for any loss or damage that may result from the use of this information, due to processing or working conditions and/or workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.

General Subfloor Preparation

1. All subfloors must be clean, smooth, flat and dry. The surface must be free of all dust, loose particles, solvents, paint, grease, oil, wax, alkali, sealing/curing compounds, old adhesive, and any other foreign material, which could affect installation. Caution: Do not use oil based sweeping compounds. Fill all depressions, cracks, and other surface irregularities with a good quality Portland cement based underlayment patching compound.

NOTE: Contamination on the substrate can cause damage to the resilient flooring material. Permanent and non-permanent markers, pens, crayons, paint, etc., must not be used to write on the back of the flooring material or used to mark the substrate as they could bleed through and stain the flooring material. If these contaminants are present on the substrate they must be mechanically removed prior to the installation of the flooring material.

Caution: Do not use liquid solvents or adhesive removers.

Johnsonite does not recommend installing UnderLock Rubber Tile over existing cushioned resilient floors.

Caution: Do not install rubber flooring in areas that are exposed to grease, oil or animal fats.

Caution: Some resilient flooring products and adhesives contain "asbestos fibers" and special handling of this material is required.

- 2. Concrete subfloors must be constructed as recommended by the American Concrete Institute's ACI 302.2 "Guide for Concrete Slabs that Receive Moisture-Sensitive Flooring Materials" and prepared to receive resilient flooring according to ASTM F 710 "Standard Practice for Preparing Concrete Floors to Receive Resilient Flooring".
 - **All concrete subfloors** must be tested for moisture prior to the installation of the flooring material:
- Moisture tests shall be conducted in accordance with ASTM F 2170 "Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs using in situ Probes".
- Moisture testing must be conducted to identify if the MVER of the concrete is within the approved limits of the patching compound manufactures specifications. (Follow the patching compound manufactures instructions for proper selection and use.)

- **3. Wood subfloors** must have a minimum 18' (47 cm) of cross-ventilated space between the bottom of the joist and ground. Exposed earth crawl spaces should be sealed with a polyethylene moisture barrier.
 - Subfloors should meet local and national building codes. Trade associations, such as the APA -"The Engineered Wood Association", offer structural guidelines for meeting various code requirements.
 - Countersink nail heads and fill depressions, joints, cracks, gouges, and chipped edges with a good quality Portland cement based patching compound.
- 4. Terrazzo and Ceramic floor surface must be thoroughly sanded to remove all glaze and waxes. Remove or replace all loose tiles and clean the grout lines. Use a Portland cement based leveling compound to fill all grout lines and other depressions.
- **5. Concrete floors equipped with a radiant heating system:** Turn the heat down to 65°F (18°C) for at least 48 hours before installation. Heat may be gradually returned to operating temperature 48 hours after installation. Temperature should not exceed 85°F (30°C).

UnderLock Tile Installation

- 1. Installation Procedure:
 - a. UnderLock tiles should not be adhered to the substrate. They are designed for loose lay installation only.
 - **b.** Square the area and establish reference points on substrate.
 - c. Lay out the tile so that a minimum of onehalf of a tile forms the border along the perimeter.
- **d.** Use established reference points and install the flooring.
- e. Start with the first row of tiles in the upper left corner of the area with 'male' tabs facing outward to receive the next tiles to be installed.
- **f.** Align the next tile to the installed tile by overlapping the 'male' tabs with the 'female' tabs.
- g. Once the tiles are properly aligned, roll the edge of the tiles with a small hand roller to secure the tabs.
- h. Cut tiles net to walls and vertical objects. Cutting tiles tight or heavy to walls and vertical objects may cause tiles to lift or peak at the seams.

Maintenance

- Initial cleaning should be performed immediately after installation.
- **2.** Since UnderLock Tiles are not adhered to the substrate, it is important to follow the
- recommended maintenance instructions using a minimal amount of water.
- Refer to Johnsonite's Maintenance Instructions for complete details.

Check Web Site (www.johnsonite.com) for current instructions.

Contact Johnsonite at (800)-899-8916 with any questions.



THE ULTIMATE FLOORING EXPERIENCE

Technical Services Department
16910 Munn Road, Chagrin Falls, Ohio 44023
(800) 899-8916 ext 9297 Fax (440) 632-5643
www.johnsonite.com
email: info@johnsonite.com
© 2012 Johnsonite Inc.

